



GOKUL EXIMP

Range of Cationic / Acrylic dyes



Shade Card

Cationic / Acrylic Dyes



GOKUL EXIMP

BRILL FLAVINE 10GFF 300%



C.I.Basic No.	Y-40	Saturation Factor	0.5	Perspiration	4-5
Dyeing Depth	0.5	Light (Xenon)	3	Rubbing	
Compatible Value	3.5	Soaping	4-5	Dry	Wet
				5	5

Yellow X-8GL 250%



C.I.Basic No.	Y-13	Saturation Factor	0.75	Perspiration	4-5
Dyeing Depth	0.9	Light (Xenon)	3-4	Rubbing	
Compatible Value	3.5	Soaping	4-5	Dry	Wet
				4-5	4-5

GOLDEN YELLOW X-GL 250%



C.I.Basic No.	Y-28	Saturation Factor	0.61	Perspiration	4-5
Dyeing Depth	0.4	Light (Xenon)	6-7	Rubbing	
Compatible Value	3	Soaping	4-5	Dry	Wet
				4-5	4-5

BRILL RED X-5GN 250%



C.I.Basic No.	R-14	Saturation Factor	0.5	Perspiration	4-5
Dyeing Depth	0.5	Light (Xenon)	3-4	Rubbing	
Compatible Value	3	Soaping	4-5	Dry	Wet
				4-5	4-5

PINK X-FG 250%



C.I.Basic No.	R-13	Saturation Factor	0.46	Perspiration	4-5
Dyeing Depth	0.61	Light (Xenon)	3-5	Rubbing	
Compatible Value	4	Soaping	4	Dry	Wet
				4-5	3-4

RED X-GRL 250%



C.I.Basic No.	R-46	Saturation Factor	0.56	Perspiration	4-5
Dyeing Depth	0.6	Light (Xenon)	6-7	Rubbing	
Compatible Value	2.5	Soaping	4-5	Dry	Wet
				4-5	4

Cationic / Acrylic Dyes

RED X-GTL 200%



C.I.Basic No.	R-18	Saturation Factor	0.72	Perspiration	4-5
Dyeing Depth	0.5	Light (Xenon)	5-6	Rubbing	
Compatible Value	2.5	Soaping	4-5	Dry	Wet
				4-5	4-5

RED VIOLET 3R 300%



C.I.Basic No.	V-16	Saturation Factor	0.78	Perspiration	4-5
Dyeing Depth	0.3	Light (Xenon)	3	Rubbing	
Compatible Value	1.5	Soaping	4-5	Dry	Wet
				4	4

BLUE X-GRRL 250%



C.I.Basic No.	B-41	Saturation Factor	0.4	Perspiration	4
Dyeing Depth	0.4	Light (Xenon)	6	Rubbing	
Compatible Value	3	Soaping	4	Dry	Wet
				4-5	4-5

BLUE X-BL 250%



C.I.Basic No.	B-159	Saturation Factor	0.43	Perspiration	4-5
Dyeing Depth	0.36	Light (Xenon)	6-7	Rubbing	
Compatible Value	3	Soaping	4-5	Dry	Wet
				4-5	4-5

TURQ BLUE X-GB 250%




C.I.Basic No.	B-3	Saturation Factor	0.75	Perspiration	4-5
Dyeing Depth	0.36	Light (Xenon)	4-5	Rubbing	
Compatible Value	3.5	Soaping	4-5	Dry	Wet
				4-5	4-5

BLACK X-FBL 300%



C.I.Basic No.	-	Saturation Factor		Perspiration	4-5
Dyeing Depth	2	Light (Xenon)	6	Rubbing	
Compatible Value	3	Soaping	4	Dry	Wet
				4-5	4



**Contact us
to get your
color needs
fulfilled.**



GOKUL EXIMP

**(STAR EXPORT HOUSE)
AN ISO 9001:2015 CERTIFIED COMPANY**

25-A Juhu Supreme Shopping Center, Gulmohar Cross Road No. 9, JVPD Scheme, Mumbai 400049, India
Phone: +91-22-66923698, 66997369 Mobile : +91-9820024339 (Naveen) / 9920459697 (Rohit)
Email: gokuleximp@gmail.com / naveen@gokuleximp.com / rohit@gokuleximp.com
Website : www.gokuleximp.com